

Overpainting and restoration of exterior BlueScope coated steel products

INTRODUCTION

NOTE: The advice provided in this Technical Bulletin is not applicable to SuperDura™ Stainless prepainted steel or COLORBOND® Metallic steel products. Please consult Steel Direct for advice on overpainting these products.

COLORBOND® prepainted steel is manufactured by BlueScope on a continuous coil paint coating line. This involves the application of high quality paint to a metallic coated steel substrate, which is then baked in a high temperature oven, to create a durable finish.

ZINCALUME® aluminium/zinc/magnesium alloy-coated steel (also manufactured by BlueScope) is supplied with a specially formulated clear resin on the surface to avoid fingerprint marks during installation. Zinc-coated steel is supplied in the passivated condition to protect against surface corrosion during storage. If required, COLORBOND® steel, ZINCALUME® steel and zinc-coated steel can be successfully overpainted. However, the following should be considered:

- Air drying paints have different weathering characteristics to COLORBOND® steel. This means that the high durability of the COLORBOND® steel finish is often not matched by air dried paints, including touch-up paint; and
- The overpainting of COLORBOND® steel, ZINCALUME® steel or zinc-coated steel will void any warranties issued by BlueScope.

- There is no texture match for COLORBOND® steel Matt and no colour match for COLORBOND® Metallic steel.

OVERPAINTING COLORBOND® STEEL, ZINCALUME® STEEL AND ZINC-COATED STEEL

- It is normal practice to ensure any surface to be painted is in a suitable condition for painting. The most appropriate preparation is dependent on the age and condition of the surface. Table 1 and 2 provide recommendations on surface preparations for COLORBOND® steel, ZINCALUME® steel and zinc-coated steel prior to overpainting.
- The most suitable paint type for overpainting BlueScope coated steel products is generally water-based acrylic. However, in more corrosive salt marine locations (refer to Technical Bulletin TB-35 Australian Salt Marine Classifications), it may be necessary to choose a paint system that has enhanced corrosion resistance (for example, inclusion of a zinc-rich primer).
- Due to ongoing improvements in paint technologies, at any one time there are numerous potentially suitable paint products available. It is therefore recommended that a reputable paint supplier be consulted to determine the most appropriate paint system for your particular application and environment.
- It is recommended that the paint supplier's safety guidelines are followed, especially

those regarding the wearing of appropriate personal protective equipment.

- Ensure conformance to local legislative requirements for "Working at Heights" and local water restrictions.
- It is recommended that paints from different suppliers are not mixed (for example, primer and topcoats).
- Note that not all post paint systems available are suitable for use in the collection of drinking water. Therefore, if a paint system is applied to a roof used for drinking water collection, ensure that it is recommended by the paint supplier for this purpose.
- Air drying paints have different weathering characteristics to oven cured prepainted products like COLORBOND® steel. Therefore, areas overpainted with air-drying paints to match adjacent COLORBOND® steel areas may weather at a different rate and vary in appearance over time.

REPAIR OF MINOR SCRATCHES AND BLEMISHES

BlueScope does not recommend the use of touch-up paint to repair damage or scratches to the painted surface. As explained above, air drying paints have different weathering characteristics to COLORBOND® steel, leading to variations in appearance over time where touch-up paint has been used. BlueScope has no recommended method for the removal of touch-up paint.

Technical Bulletin 2

January 2021. Revision 13.
This issue supersedes all previous issues.



Minor scratches (< 2mm in width and unnoticeable from ground level) should be left alone as the available metallic coating will protect against corrosion. If scratches are more noticeable on new material, it is the recommendation of BlueScope to replace the affected product.

Galling is generally only superficial damage caused by painted surfaces rubbing together as a result of vibration and inter-sheet movement during transport.
Treat as per minor scratches.

RELATED TECHNICAL BULLETINS

[Technical Bulletin TB-5](#)
Swarf staining of steel profiles

[Technical Bulletin TB-35](#)
Australian salt marine classifications

[Technical Bulletin-38](#)
Effect of touch-up paint

Table 1: Recommended surface preparation for COLORBOND® steel

CONDITION	RECOMMENDED PREPARATION
Brand new (typically less than 1 year of weathering)	Mechanical abrasion 1. Using a mop or a soft nylon bristle broom, wash the COLORBOND® steel surface with household detergent and water to remove all major loose particles that may damage the surface in subsequent procedures. Rinse thoroughly with fresh potable water and allow surface to dry. 2. Slightly roughen the surface lightly with kitchen scourer pads (not steel wool) to provide a "key" to enhance adhesion of the selected paint finish by removing surface gloss. Take care not to remove the existing paint surface on bends. Do not use steel wool as an abrasive medium as it will generate swarf (small metallic particles), which will damage the material surface (refer to Technical Bulletin TB-5 Swarf staining of steel profiles). 3. Using a mop or a soft nylon bristle broom, wash the COLORBOND® steel surface with household detergent and water. Rinse thoroughly with fresh potable water and allow surface to dry. Note: when overpainting COLORBOND® steel Matt, the surface finish will be altered via this surface preparation. It is recommended to prepare and apply paint in a test area first.
Aged (typically more than 1 year of weathering)	Natural weathering — After 1-2 years of service COLORBOND® steel will typically have a uniformly weathered surface as indicated by a slight reduction in gloss appearance. A uniformly weathered surface should provide adequate adhesion of the selected paint finish. Using a mop or a soft nylon bristle broom, wash the COLORBOND® steel surface with household detergent and water. Rinse thoroughly with fresh potable water and allow surface to dry. Note: when overpainting aged COLORBOND® steel Matt, the surface finish will be altered via this surface preparation. It is recommended to prepare and apply paint in a test area first.

Table 2: Recommended surface preparation for ZINCALUME® steel and zinc-coated steel

CONDITION	RECOMMENDED PREPARATION
Brand new or evenly weathered surface (usually well washed)	Using a mop or a soft nylon bristle broom, wash the surface with household detergent and water. Rinse thoroughly with fresh potable water and allow surface to dry.
Damaged areas (i.e. corrosion product evident)	Repair of damaged areas where base metal has been exposed and rust is apparent, can be undertaken by first removing all rust thoroughly with a stiff nylon bristle brush. (NOTE: Care should be taken to only remove corrosion products and not the metallic coating.) Sweep away all loose particles, then thinly apply a zinc rich etch primer from a reputable paint supplier.

NOTE: The condition of the surface will depend on a number of factors, in particular product age, orientation (i.e. north, south, east or west facing), environment, exposure and application.

OVERPAINTING THE SURFACE

Apply the selected paint finish to the clean prepared surface. Ensure manufacturer's instructions are followed, especially with regard to application and film thickness. It is recommended to check your colour choice when overpainting COLORBOND® steel Matt, as the surface preparation step may alter the micro-textured surface. NOTE: The overpainting of COLORBOND® steel, ZINCALUME® steel or zinc-coated steel will void any warranties issued by BlueScope. Should, for any reason, overpainting be undertaken on behalf of and under instruction from BlueScope, then a future warranty (if any) position will be as negotiated between the customer and BlueScope.

steel.com.au

To ensure you have the most current Technical Bulletin

1800 800 789

steeldirect@bluescopesteel.com

If you have any questions regarding this Bulletin, contact Steel Direct



*Warranties are subject to exclusions, application and eligibility criteria. For full terms and conditions and to determine the eligibility of your product for the warranty visit www.bluescopesteel.com.au/warranties or contact Steel Direct. The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements. BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin. COLORBOND®, ZINCALUME®, BlueScope and the BlueScope brand mark are registered trademarks and SuperDura™ is a trademark of BlueScope Steel Limited.

© 2021 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.